

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

A9

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D04B 1/14, D03D 15/00	A1	(11) International Publication Number: WO 97/04152 (43) International Publication Date: 6 February 1997 (06.02.97)
(21) International Application Number: PCT/EP96/03107 (22) International Filing Date: 11 July 1996 (11.07.96) (30) Priority Data: 9500630 14 July 1995 (14.07.95) BE (71) Applicant (for all designated States except US): N.V. BEKAERT S.A. [BE/BE]; Bekaertstraat 2, B-8550 Zwevegem (BE). (72) Inventors; and (75) Inventors/Applicants (for US only): DEWAEGHENEIRE, Gabriël [BE/BE]; Watmolenstraat 19, B-8550 Zwevegem (BE). VANSTEENKISTE, Philip [BE/BE]; Boerderijstraat 8, B-8540 Deerlijk (BE). VAN STEENLANDT, Wim [BE/BE]; Nachtegalenlaan 10, B-9100 Sint-Niklaas (BE). (74) Agents: RYCKEBOER, Leo et al.; N.V. Bekaert S.A., Bekaertstraat 2, B-8550 Zwevegem (BE).		(81) Designated States: CA, CN, JP, KP, KR, MX, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: TEXTILE FABRIC COMPRISING BUNDLES OF MACHINED METAL FILAMENTS (57) Abstract The invention relates to a textile fabric comprising bundles made up of metal filaments obtained by a machining process and having an equivalent filament diameter of between 15 and 150 μm and in which the filaments are disposed in a nearly parallel arrangement in the bundles. It also relates to a method for manufacturing the fabric, in particular by means of flat knitting, and to its utilization as a membrane for gas burners.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

TEXTILE FABRIC COMPRISING BUNDLES OF MACHINED METAL FILAMENTS

The invention relates to a textile fabric comprising metal filament bundles obtained by machining or shaving.

5

Background of the invention

From U.S. patent 4,930,199 a method is known for manufacturing thin metal filaments by machining, shaving or cutting them off the end face of a thin metal foil coiled around a mandrel. This produces a bundle of nearly parallel filaments with a predominantly quadrilateral cross-section, the equivalent cross-section of which is between 15 and 150 μm , depending on the thickness of the foil and the cutting speed of the shaving or cutting tool. By equivalent diameter is meant here the diameter of the circle which has the same surface area as the quadrilateral cross-section of the filament.

Since these machined filaments often have a lower tensile strength and are less straight than drawn filaments, they are difficult to process into filament yarns by twisting at the usual speeds.

Purpose and Object of the invention

It is therefore an object of the invention to provide a textile fabric comprising bundles of thin metal filaments or metal fibres which are twisted only slightly if at all and which are obtained by means of a machining process. The term textile fabric here refers to a structure which comprises a series of meshes or openings and filament bundles which define the mesh boundaries, such as woven, knitted, knotted, interwoven or tufted structures.

35

Further, it is an object of the invention to provide a method for manufacturing a textile fabric out of said bundles of thin filaments or fibres in which twisting operations on the bundles are avoided. The rather voluminous bundle of nearly
5 parallel filaments produced by the machining apparatus therefore needs to be densified or compacted in another manner in order afterwards to be processed into a textile fabric by means of knitting, weaving, braiding, knotting or tufting.

10 Moreover, whenever the initial voluminous character of the machined bundle may afterwards need to be somewhat restored in the textile fabric, the effect of this compaction or consolidation treatment should at least partly be capable of being reversed. For certain applications, it is precisely the
15 intention to obtain or preserve a relatively voluminous character in the textile fabric, for example with a view to achieving a certain flexibility in the fabric.

The invention therefore provides a textile fabric comprising
20 bundles of metal filaments obtained by means of a machining process in which these filaments have an equivalent filament diameter of between 15 and 150 μm and are disposed in a nearly parallel arrangement in the bundles. The term 'filaments' here refers both to continuous filaments and staple
25 fibres.

The method according to the invention for the manufacture of the textile fabric comprises the consolidation of the
30 machined filament or fibre bundles by means of a binding agent and the processing of the consolidated bundles into a textile fabric by means of, for example, weaving, knitting or braiding. If so desired, this binding agent can afterwards be removed in order, for example, to restore at least partially the original voluminous character of the bundle. By the term
35 binding agent is meant, on the one hand, a self-supporting filament-shaped or ribbon-shaped object that, for example, as

a binding agent can be wrapped in a spiral form around the bundle (wrapping). On the other hand, it can be a glue with which the bundle is covered or enveloped. Depending on its composition, the binding agent can be removed, for example, by means of dissolving, melting off, vaporizing, freezing out, oxidizing or burning away, by pyrolysis, carbonization, or by other chemical reactions.

The invention also relates to the metal filament or fibre bundle itself obtained by machining, and which is consolidated by means of a binding agent and can be utilized, for example, in the method for manufacturing the textile fabric. The textile fabric according to the invention can be utilized for a broad range of applications, each depending on the suitable choice of composition, structure and properties of the metal filaments, of the bundles, in some cases of the binding agent, and of the final structure of the textile fabric.

The metal filaments in the bundles can be of copper, brass, titanium, different types of stainless steel, nickel alloys and other specific types of steel containing, for example, chromium, aluminium and/or nickel and 0.05 to 0.3 % by weight of yttrium, cerium, lanthanum or titanium. The latter steels are very resistant to high temperatures (FeCr alloy, NiCr alloy, Aluchrome) and can therefore be used, for example, in burner membranes, as will be explained below. If the coiled metal foils from which the filaments have to be machined possess a coating layer which is of a different composition than that of the foil itself and which is capable of being machined, then upon machining one obtains bi- or multi-component filaments.

Upon consolidating the bundle, for example, with a binding filament such as described above, one or more other filaments or yarns can, if required, be joined under the binding

filament parallel with the metal bundle in order to improve the processability into a textile fabric or in order to fulfil specific functional requirements of the heterogeneous bundle thus obtained and/or of the final textile fabric. It is also possible to manufacture heterogeneous textile fabrics by incorporating other yarn structures into the fabric in addition to (and separately from) the consolidated metal filament bundles. Textile fabrics can also be given a heterogeneous character by constructing limited zones with mutually distinct structures throughout the thickness of these fabrics and/or in their surface, whether or not in combination with the utilization of different types of yarns and/or metal filament bundles. These substructures can then differ from one another in terms of elasticity, compressibility, density, hairiness, smoothness, stiffness, etc. Such structures can be produced for example with flat knitting machines such as the CMS 440 manufactured by the Stoll company (Germany) or the MC7 manufactured by the Universal company.

The consolidated bundles can be used as warp and/or as weft material in all kinds of weaving processes. They can be interwoven into a network, tufted or knitted into weft or warp knitted fabrics on circular or flat knitting machines and on warp knitting machines, including the Rachel machines. The weight of the fabric can be between 300 and 4,000 g/m² and in particular below 2,500 g/m². Said bundles can, according to a preferred embodiment, be incorporated into a double-bed flat or circular knitted structure, for example for preventing the edges of the fabric from rolling up.

The invention relates in particular to specific knitted fabrics made of metal filaments or fibres which are resistant to high temperatures and which, surprisingly enough, turn out to be outstanding for use as burner membranes in gas burners, both for surface radiation systems (100 kW/m² and higher) and for blue-flame systems (up to 10,000 kW/m²).

- 5 -

All this will now be explained on the basis of a number of possible embodiments for a knitted fabric which can be used, for example, as a burner membrane.

5 Detailed description of embodiments

10 A filament bundle with a metric number (Nm) of between 0.2 and 0.4 is manufactured out of a FeCr alloy with 0.1 % yttrium by weight in accordance with the machining method described in the U.S. patent 4,930,199. The utilization in burner membranes of metal fibres of these alloys and obtained by bundled drawing is itself already known, for example, from the European patent 0,390,255 of the applicant. The equivalent filament diameter of the machined fibres herein presented is between 25 and 50, e.g. approximately 36 μm . A number of these bundles are joined together and stretch broken on a drafting frame into a fibre sliver. A number of slivers are then once again joined together and, after a further drafting operation, again consolidated by the wrapping in a so-called wrapping device of the thus obtained bundle of nearly parallel fibres, for example, with a continuous synthetic filament (as binding agent) with a wrapping speed of between 200 and 500 revolutions/minute. Just previous to wrapping, a fibre core can, if needed, be inserted between the slivers on the drafting frame. The proportion of metal in this consolidated bundle can be between 0.5 and 5. It is by preference between Nm 1.5 and 5.

30 The thus consolidated bundles are processed on a flat knitting machine (5 to 14 gauge) into a double-bed knitted structure in order better to prevent the subsequent rolling up of the edges of the fabric. The fabric can have a weight between 800 and 2,000 g/m^2 e.g. about 1,200 g/m^2 . The heavier fabrics offer a longer life time. The knitted fabric has preferably a thickness of approximately 2 mm and a weight of 800 to 35 1,500 g/m^2 . The construction of the knitted structure can be

fairly simple (e.g. interlock and tubular at gauge 7). Synthetic support threads can also be added during knitting in order to facilitate the knitting process. The binding agent (and other non-metallic threads, if any) are then removed by
5 burning them away, thus leaving a knitted fabric in which the voluminosity of the original machined bundle is partially restored. After removal of the binding agent it can also be useful to roll or isostatically compress the knitted fabric in order, for example, to obtain an even more uniform permea-
10 bility in the fabric.

This knitted fabric is then fixed on a framework in the housing of a premix gas burner in the known manner as a flat or tubular membrane at the level of the flame. Such gas
15 burners are illustrated i.a. in WO 93/18342 of applicant. A conventional propane/air mixture (with stoichiometric mixing proportions and with an excess of air, respectively) is delivered to the burner. It is put into operation for prolonged periods of time with successive cycles ranging from a surface
20 radiation system to a blue-flame system, with sudden interruptions in between. It turns out that the gas permeability of the fabric makes it possible to have a uniform burning front without backfiring of the flame and without generating whistling tones at high flow rates. This is therefore an
25 indication of a good temperature separation between the inlet and the outlet sides of the gas through the membrane. In any case, the emission values for CO and NO_x remain low during operation. A pressed or rolled membrane fabric can be recommended, if such should be needed.

30 This knitted structure offers the advantage that, in contrast to the usual sintered thin membranes, it is pliable. Thus the well-known problem of expansion of the rigid sintered membrane plates is avoided. In addition, the knitted fabrics can
35 be supplied in large surface areas in rolled-up form. This makes it possible to keep the losses low by cutting up the

5 fabric. If knitted Rachel fabrics are utilized, the mesh opening will have to be kept between 0.5 and 5 mm. In particular surface zones of the membrane, the mesh density can be made different from those in adjacent surface zones in order thus to create different local burning systems in the membrane, depending on the gas flow rate used.

10 Compared to sintered metal fiber burner membranes, the knitted structures offer in addition the advantage that they heat up much more rapidly. It is thus possible, with the fabrics according to the invention to generate very intense heating pulses lasting e.g. less than one second. This interesting feature enables e.g. the use of the fabrics of the invention in certain sections of furnaces for bending glass sheets.
15 Such furnaces may then include zones with differential heating as disclosed e.g. in EP 0,659,697.

20 Within the framework of the invention, it is also possible to consider utilizing knitted Bekitherm fabrics (e.g. types KNC1, KNC3) from the applicant as burner membrane. These fabrics are made of metal fibres (e.g. of FeCrAlloy) which are obtained by a process of bundled drawing such as is described in U.S. patent 3,379,000 and which have an equivalent diameter of between 4 and 50 μm . This bundle of parallel
25 metal filaments, which is obtained after a leaching treatment of the bundle composite, can be spun into yarn. Before knitting, however, these bundles can also be wrapped with binding filaments according to the method of the invention. If so desired, two or more yarns or wound bundles can be twisted together for knitting or weaving in order to obtain the desired yarn titres. The yarns or wrapped bundles made up of bundled drawn metal fibres can of course also be processed on
30 a flat knitting machine into a double-bed structure such as described above for the bundles made up of machined fibres. Other metal raw materials may of course be considered for use
35 in applications other than burner membranes.

- 8 -

The textile fabrics of the invention can also be used as filter sheets to trap the coarse particles in hot gas streams. They can also be used as heat shields or curtains at the entree or exit of tunnel furnaces.

5

The fabrics can also be used to polish e.g. stainless steel surfaces by friction. A tubular knit fabric can e.g. be sleeved on a bar or rod or tube to polish its outer surface by a rubbing treatment.

10

When coated with catalytically active substances, the fabrics can act as a support sheet for such catalysts in reactors. The fabrics can also be used as a supporting layer in airbag filters.

15

CLAIMS

5 1. A textile fabric comprising bundles made up of metal filaments obtained by a machining process, with an equivalent filament diameter of between 15 and 150 μm , and in which the filaments are disposed in a nearly parallel arrangement in the bundles.

10 2. A textile fabric according to claim 1 characterized in that it is knitted and that it has a weight of between 300 and 4,000 g/m^2 .

15 3. A textile fabric according to claim 1 characterized in that it is compressed by rolling or by isostatic pressing.

 4. A textile fabric according to claim 2 characterized in that it has a double-bed flat or circular knitted structure.

20 5. A flat knitted textile fabric according to claim 4 in which the equivalent filament diameter is between 25 and 50 μm and in which the proportion of metal in the bundles is between Nm 0,5 and 5.

25 6. A textile fabric according to claim 5 with a weight of between 800 and 2,000 g/m^2 .

30 7. A textile fabric according to claim 1 comprising bundles of stainless steel filaments.

 8. A textile fabric according to claim 1 comprising bundles of titanium filaments.

35 9. A textile fabric according to claim 1 comprising filaments made up of steel alloys containing chromium, aluminium and between 0.05 and 0.3 % yttrium by weight.

10. A method for manufacturing the textile fabric according claim 1 comprising the consolidation of the filament bundles by means of a binding agent and the processing of the consolidated bundles into a textile fabric by means of weaving, knitting or braiding.

11. A method according to claim 10 in which the binding agent is afterwards removed from the textile fabric.

12. A metal fibre bundle consolidated with a binding agent and intended for use in the method according to claim 10.

13. A bundle which is wrapped with a binding agent and which is made up of nearly parallelly arranged machined metal filaments with an equivalent filament diameter of between 25 and 50 μm and in which the proportion of metal in the bundle is between Nm 0,5 and 5.

14. The utilization of a textile fabric according to claim 9 as a gas burner membrane.

15. The utilization of a textile fabric according to claim 6 as a gas burner membrane comprising filaments made up of steel alloys containing chromium, aluminium and between 0.05 and 0.3 % yttrium by weight.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 96/03107

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 D04B1/14 D03D15/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 D04B D03D D04C B23P F23D D02G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,93 09940 (MEMTEC AMERICA CORPORATION) 27 May 1993	
A	WO,A,94 01373 (N.V. BEKAERT S.A.) 20 January 1994	
A	US,A,4 930 199 (YANAGISAWA) 5 June 1990 cited in the application	
A	EP,A,0 390 255 (N.V. BEKAERT S.A.) 3 October 1990 cited in the application	

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

* & * document member of the same patent family

Date of the actual completion of the international search

8 November 1996

Date of mailing of the international search report

20. 11. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Van Gelder, P

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 96/03107

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9309940	27-05-93	US-A- 5248548	28-09-93
		AU-B- 662786	14-09-95
		AU-A- 3144793	15-06-93
		CA-A- 2101087	23-05-93
		EP-A- 0568688	10-11-93
		JP-T- 6504744	02-06-94
		US-A- 5287690	22-02-94

WO-A-9401373	20-01-94	BE-A- 1006069	03-05-94
		AU-A- 4301893	31-01-94

US-A-4930199	05-06-90	JP-A- 1316137	21-12-89
		CN-A- 1036352	18-10-89
		CN-B- 1029299	12-07-95
		DE-A- 3880451	27-05-93
		DE-T- 3880451	25-11-93
		EP-A- 0319959	14-06-89
		CA-A- 1320616	27-07-93

EP-A-0390255	03-10-90	AT-T- 126579	15-09-95
		CA-A- 2012261	29-09-90
		DE-D- 69021609	21-09-95
		DE-T- 69021609	01-02-96
		JP-A- 3110312	10-05-91
		US-A- 5088919	18-02-92
